

AD-A243 487



COMPARISONS OF SELF-ASSEMBLED MONOLAYERS ON SILVER AND GOLD:
MIXED MONOLAYERS DERIVED FROM $\text{HS}(\text{CH}_2)_{21}\text{X}$ AND $\text{HS}(\text{CH}_2)_{10}\text{Y}$
(X, Y = CH_3 , CH_2OH) HAVE SIMILAR PROPERTIES

Paul E. Laibinis, Marye Anne Fox, John P. Folkers, and
George M. Whitesides
Department of Chemistry
Harvard University
Cambridge MA 02138

DTIC
ELECT
DEC 17 1991
S C J

Technical Report No. 42 (December 1991)

Interim Technical Report
(Accepted for publication in Langmuir)

PREPARED FOR DEFENSE ADVANCED RESEARCH PROJECTS AGENCY
1400 Wilson Boulevard
Arlington VA 22209

DEPARTMENT OF THE NAVY
Office of Naval Research, Code 1130P
800 North Quincy Street
Arlington VA 22217-5000

Project No.: a400011dd205
Contract No.: N00014-86-K-0756
Effective Date: 86 September 15
Expiration Date: 92 September 14

91-18204



Principal Investigator: George M. Whitesides
(617) 495-9430

The views and conclusions in this document are those of the authors and should not be interpreted as necessarily representing the official policies, either expressed or implied, of the Defense Advanced Research Projects Agency or the U.S. Government.

DISTRIBUTION STATEMENT A

Approved for public release;
Distribution Unlimited

91 18204

REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

1a. REPORT SECURITY CLASSIFICATION Unclassified			1b. RESTRICTIVE MARKINGS		
2a. SECURITY CLASSIFICATION AUTHORITY			3. DISTRIBUTION / AVAILABILITY OF REPORT Approved for public release; distribution unlimited		
2b. DECLASSIFICATION / DOWNGRADING SCHEDULE					
4. PERFORMING ORGANIZATION REPORT NUMBER(S) Technical Report No. 42			5. MONITORING ORGANIZATION REPORT NUMBER(S)		
6a. NAME OF PERFORMING ORGANIZATION Harvard University		6b. OFFICE SYMBOL (if applicable)	7a. NAME OF MONITORING ORGANIZATION DARPA		
6c. ADDRESS (City, State, and ZIP Code) Office for Sponsored Research Holyoke Center, Fourth Floor Cambridge MA 02138-4993			7b. ADDRESS (City, State, and ZIP Code) 1400 Wilson Boulevard Arlington VA 22209-2308		
8a. NAME OF FUNDING / SPONSORING ORGANIZATION ONR		8b. OFFICE SYMBOL (if applicable)	9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER		
8c. ADDRESS (City, State, and ZIP Code) Chemistry Division, Code 1113 Office of Naval Research Arlington VA 22217-5000			10. SOURCE OF FUNDING NUMBERS		
			PROGRAM ELEMENT NO. 86-K-0756	PROJECT NO.	TASK NO. a400011dd2
					WORK UNIT ACCESSION NO.
11. TITLE (Include Security Classification) "Comparison of Self-Assembled Monolayers on Silver and Gold:"					
12. PERSONAL AUTHOR(S) P. Laibinis, M. Fox, J. Folkers, and G. Whitesides					
13a. TYPE OF REPORT Technical		13b. TIME COVERED FROM _____ TO _____		14. DATE OF REPORT (Year, Month, Day) December 1991	
15. PAGE COUNT					
16. SUPPLEMENTARY NOTATION					
17. COSATI CODES			18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)		
FIELD	GROUP	SUB-GROUP			
19. ABSTRACT (Continue on reverse if necessary and identify by block number)					
<p>This paper describes the preparation of self-assembled monolayers (SAMs) by adsorption of alkanethiols on evaporated silver, and compares these SAMs with analogous SAMs prepared on gold. The work concentrated on SAMs derived from mixtures of alkanethiols having long and short chains and terminating in hydrophobic and hydrophilic tails: HS(CH₂)₁₀CH₃, HS(CH₂)₂₁CH₃,</p>					
20. DISTRIBUTION / AVAILABILITY OF ABSTRACT <input type="checkbox"/> UNCLASSIFIED/UNLIMITED <input checked="" type="checkbox"/> SAME AS RPT <input type="checkbox"/> DTIC USERS			21. ABSTRACT SECURITY CLASSIFICATION Unclassified		
22a. NAME OF RESPONSIBLE INDIVIDUAL Dr. Harold Guard			22b. TELEPHONE (Include Area Code) 703/696-4311		22c. OFFICE SYMBOL

HS(CH₂)₁₀CH₂OH, and HS(CH₂)₂₁CH₂OH. The thickness and the compositions of these SAMs were established by X-ray photoelectron spectroscopy (XPS). As is observed with self-assembled alkanethiolate monolayers on gold, the composition of the monolayers parallels but does not equal the solution composition. Less pronounced differences are observed between compositions in solution and on the surface on silver than have previously been reported on gold. Rates of exchange of surface thiolates with thiols in solution are similar on silver and gold. This similarity suggests that the differences between the compositions of the mixed SAMs formed from solutions having the same composition by adsorption on silver and gold are due to factors important during the initial formation of these monolayers, rather than during their subsequent equilibration. Although mixtures of thiols are probably not adsorbed in a completely random fashion on silver, no evidence could be found for the formation of discrete, separate phases on the surface (i.e. islands). Measurements of surface wettability (via contact angle measurement with water and hexadecane) exhibit departures from Cassie's expression indicating appreciable disorder in the hydrocarbon chains at the monolayer/liquid interface. The wettability of SAMs on silver by water and hexadecane were similar to those formed on gold having the same composition.

REVISED

Comparisons of Self-Assembled Monolayers on Silver and Gold: Mixed Monolayers Derived from $\text{HS}(\text{CH}_2)_{21}\text{X}$ and $\text{HS}(\text{CH}_2)_{10}\text{Y}$ ($\text{X}, \text{Y} = \text{CH}_3, \text{CH}_2\text{OH}$) Have Similar Properties.¹

Paul E. Laibinis[†], Marye Anne Fox[§], John P. Folkers[†], and George M. Whitesides^{†*}

Department of Chemistry
Harvard University
Cambridge, Massachusetts 02138

and

Department of Chemistry
University of Texas at Austin
Austin, Texas 78712-1167

Accession For	
NTIS Grant	<input checked="" type="checkbox"/>
DTIC Tab	<input type="checkbox"/>
Unpublished	<input type="checkbox"/>
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	

[†]Harvard University

[§]University of Texas at Austin

Abstract

This paper describes the preparation of self-assembled monolayers (SAMs) by adsorption of alkanethiols on evaporated silver, and compares these SAMs with analogous SAMs prepared on gold. The work concentrated on SAMs derived from mixtures of alkanethiols having long and short chains and terminating in hydrophobic and hydrophilic tails: $\text{HS}(\text{CH}_2)_{10}\text{CH}_3$, $\text{HS}(\text{CH}_2)_{21}\text{CH}_3$, $\text{HS}(\text{CH}_2)_{10}\text{CH}_2\text{OH}$, and $\text{HS}(\text{CH}_2)_{21}\text{CH}_2\text{OH}$. The thickness and the compositions of these SAMs were established by X-ray photoelectron spectroscopy (XPS). As is observed with self-assembled alkanethiolate monolayers on gold, the composition of the monolayers parallels but does not equal the solution composition. Less pronounced differences are observed between compositions in solution and on the surface on silver than have previously been reported on gold. Rates of exchange of surface thiolates with thiols in solution are similar on silver and gold. This similarity suggests that the differences between the compositions of the mixed SAMs formed from solutions having the same composition by adsorption on silver and gold are due to factors important during the initial formation of these monolayers, rather than during their subsequent equilibration. Although mixtures of thiols are probably not adsorbed in a completely random fashion on silver, no evidence could be found for the formation of discrete, separate phases on the surface (i.e. islands). Measurements of surface wettability (via contact angle measurement with water and hexadecane) exhibit departures from Cassie's expression indicating appreciable disorder in the hydrocarbon chains at the

monolayer/liquid interface. The wettability of SAMs on silver by water and hexadecane were similar to those formed on gold having the same composition.

Introduction

This paper describes methods of controlling the wettability and thickness of thin organic films (self-assembled monolayers, SAMs²) adsorbed on silver. These SAMs were derived from solutions containing mixtures of two alkanethiols, one having a chain length longer than the other. We have previously described our studies of these systems adsorbed on gold.³⁻⁵ Here we extend these studies to SAMs on silver and contrast the properties of these films with those formed on gold. Alkanethiolate monolayers formed on gold and silver have related but different structures;⁶⁻⁹ they may exhibit different macroscopic properties. Wetting is a property that is sensitive to microscopic changes in composition,¹⁰⁻¹² morphology,¹³ and functionality.^{2,14-17} In this paper, we examine the response of wetting to the structural differences present in mixed SAMs on silver and gold.

Long chain alkanethiols ($\text{HS}(\text{CH}_2)_n\text{X}$) adsorb from solution onto silver^{6-9,14} and gold¹⁴⁻²³ surfaces and form oriented, densely packed monolayers. On both gold and silver, the hydrocarbon chains have been shown by polarized infrared external reflectance spectroscopy (PIERS) to be largely trans-extended and highly crystalline^{6-8,18,20} although both theory^{24,25} and experiment^{6,20-22} indicate that gauche conformers exist and are concentrated at the terminal C-C bonds. The monolayers are, however, structurally slightly different: on gold,^{6,18,20} the axis of the hydrocarbon chain is canted at an angle of $\sim 28^\circ$ relative to the surface normal;²⁷ on silver,⁶⁻⁹ the alkanethiolate chain is canted $\sim 12^\circ$ relative to the surface normal. The cant angles are believed to

result from interchain spacings that are imposed on the monolayer by the metal/sulfur lattice.^{6,28} The packing density of alkyl thiolates is greater on silver than on gold, and a much lower population of gauche conformers is present on silver at room temperature than on gold.⁶

On both silver and gold, a variety of tail groups can be accommodated in the SAMs.^{2,14-16,20} These surfaces can be hydrophobic ($\theta_a^{\text{H}_2\text{O}} \approx 115^\circ$ for $X = \text{CH}_3, \text{CF}_3$) or hydrophilic ($\theta_a^{\text{H}_2\text{O}} < 15^\circ$ for $X = \text{OH}, \text{CO}_2\text{H}, \text{CONH}_2$); intermediate values of wettability can be obtained by employing tail groups of intermediate polarity (for example, $X = \text{CO}_2\text{CH}_3, \text{Cl}, \text{CN}$) or by generating surfaces composed of a mixture of hydrophobic and hydrophilic tail groups.^{12,14} We have recently compared the wetting properties of SAMs on silver and gold derived from $\text{HS}(\text{CH}_2)_n\text{X}$ and from mixtures of $\text{HS}(\text{CH}_2)_{11}\text{CH}_3$ and $\text{HS}(\text{CH}_2)_{11}\text{OH}$; we found no differences in wetting that could be attributed to differences in the structure of the SAMs.¹⁴ The difference in the structure of SAMs of alkyl thiolates on gold and silver has not yet been shown to cause a difference in their properties.²⁹

The objective of this work was to search for such a difference using a property -- wettability -- in a system in which wetting has been demonstrated repeatedly to be sensitive to small variations in the structure of the SAM at its interface with liquid.^{3-5,30} The most sensitive system presently available -- SAMs derived from mixtures of two *n*-alkanethiols having different chain lengths -- has allowed detection of changes in surface composition and order by wetting.³⁻⁵ On gold, these systems do not

form macroscopic islands (although they may form small phase-separated clusters of thiolates on the same species) and appear by IR spectroscopy to present a disordered structure at the solid-vapor interface while the bulk of the underlying monolayer remains crystalline.³¹

We examined mixed monolayers on silver derived from four *n*-alkanethiols: $\text{HS}(\text{CH}_2)_{10}\text{CH}_3$, $\text{HS}(\text{CH}_2)_{10}\text{CH}_2\text{OH}$, $\text{HS}(\text{CH}_2)_{21}\text{CH}_3$, and $\text{HS}(\text{CH}_2)_{21}\text{CH}_2\text{OH}$. We refer to these compounds, when components of SAMs, by the termini of the shorter and longer thiols (for $n = 10$, Sh = short; $n = 21$, Lg = long); for example, Sh = CH_2OH /Lg = CH_3 refers to monolayers derived from mixtures containing $\text{HS}(\text{CH}_2)_{10}\text{CH}_2\text{OH}$ and $\text{HS}(\text{CH}_2)_{21}\text{CH}_3$. The differences in the chain lengths and tail groups of the adsorbates provide easily detectable differences in thickness and wettability. This paper compares the wettability of mixed SAMs derived from mixtures of these compounds on silver and gold, and uses these data to infer comparative details of their structures.

The systems formed on gold are dynamic and the surface composition of the monolayer increases in the longer alkanethiol with continued exposure to the contacting solution.^{4,5} We standardized our adsorption times (1 d) and concentrations (1 mM as the sum of the concentrations of all thiols in solution) to allow direct comparison with results obtained on gold under these conditions. We also examined the surface compositions formed from longer adsorption times. To allow analysis of differences in the adsorption characteristics on silver and gold, we compared the

rates of exchange of surface thiolates on gold and silver with thiols in solution.

For the four sets of mixed monolayers studied, we reference both the XPS and wetting data to compositions of thiols in solution, since these compositions represent the primary experimental data. We plot wetting data as $\cos \theta$ since $\cos \theta$ is linearly related to the interfacial free energy by Young's equation³² (eq 1).

$$\cos \theta = \frac{\gamma_{SV} - \gamma_{SL}}{\gamma_{LV}} \quad (1)$$

We also compare the wettability of the monolayers with their surface composition (χ_n = surface mole fraction of component n). Wetting, expressed as $\cos \theta$, has been related to the composition of heterogeneous surfaces by Cassie¹⁰ (eq 2) and Israelachvili and Gee¹¹ (eq 3)

$$\cos \theta = f_1 \cos \theta_1 + f_2 \cos \theta_2 \quad (2)$$

$$(1 + \cos \theta)^2 = f_1 (1 + \cos \theta_1)^2 + f_2 (1 + \cos \theta_2)^2 \quad (3)$$

where f_1 and f_2 are the fractional areas occupied by components 1 and 2, and θ_1 and θ_2 are the wetting properties of pure surfaces of 1 and 2. The adsorbates we employ can occupy different relative areas of the surface and values of f_n and χ_n may be related but different.

Methods

Determination of the Surface Composition of Two-component SAMs. The ratio of alkyl thiolates in a mixed SAM is often different from the ratio of thiols in the solution from

which it was formed.^{3-5,12,14} To determine the surface composition (χ_n), we assume that the thickness (d) of a monolayer composed of two alkyl thiolates is a simple weighted average of the thicknesses of SAMs derived from the individual thiols (eq 4: sh = shorter thiolate; lg = longer thiolate).

$$d = \chi_{sh} d_{sh} + \chi_{lg} d_{lg} \quad (4)$$

Eq 4 assumes that the packing density of alkyl thiolates does not change with surface composition; tail groups commensurate in size with the polymethylene chain (e.g., CH_3 and CH_2OH) should have no effect on the packing density of the monolayer.²⁰ We estimate the surface composition by comparing the thickness of a mixed monolayer to the thicknesses of SAMs derived from the individual components (eq 5).³³

$$\chi_{lg} = \frac{d - d_{sh}}{d_{lg} - d_{sh}} \quad (5)$$

Relationship Between Thickness of Alkanethiolate Monolayers on Silver and $\ln(\text{C}(1s)/\text{Ag}(3d))$. Thicknesses of SAMs have been estimated by a variety of techniques.³⁴ For these systems on silver, we find XPS to be a convenient and highly reproducible method of estimating the thicknesses of the SAMs. We estimate thicknesses comparing the intensity of peaks due to $\text{C}(1s)$ and $\text{Ag}(3d)$ and relate these thicknesses to surface compositions using eq 5. Figure 1 is a schematic illustration of an alkanethiolate monolayer on silver. The XPS intensities of the $\text{C}(1s)$ and $\text{Ag}(3d)$ peaks can be described by eq 6 and 7,




Figure 1. Schematic illustration of an *n*-alkanethiolate monolayer adsorbed on silver.

$$C_d = C_\infty(1 - e^{-d/\lambda_1 \sin \phi}) \quad (6)$$

$$Ag_d = Ag_\infty S(e^{-d/\lambda_2 \sin \phi}) \quad (7)$$

where C_d is the intensity of the C(1s) photoelectrons due to the monolayer of thickness d ; Ag_d is the intensity of the Ag(3d) photoelectrons attenuated by the alkanethiol monolayer of thickness d ; C_∞ and Ag_∞ are the intensities of photoelectrons (C(1s) and Ag(3d), respectively) expected for infinitely thick layers of hydrocarbon and silver, respectively; d is the thickness of the hydrocarbon portion of the monolayer; λ_1 and λ_2 are the attenuation lengths of photoelectrons due to C(1s) and Ag(3d) through a hydrocarbon film, respectively -- we estimate these parameters to equal 35 and 34 Å, respectively;³⁵ ϕ is the angle between the analyzer and the surface (the take-off angle, here is 35°); S is a term that corrects the silver signal for attenuation by the adsorbed sulfur.

Taking the logarithm of the ratio of eq 6 and 7 yields eq 8

$$\ln\left(\frac{C_d}{Ag_d}\right) = \frac{d}{\lambda_2 \sin \phi} + \ln(1 - e^{-d/\lambda_1 \sin \phi}) + K \quad (8)$$

where the constant $K = \ln(C_\infty/Ag_\infty S)$. The constant contains terms that are dependent on instrumental parameters, and its value is not important for our analysis. Eq 8 is composed of a term linear in thickness and a term that remains approximately constant at sufficiently high values of d to have a negligible effect on the "slope" of the function. Figure 2 contains a plot of the function given in eq 8 ($K = 1.75$) over the range of thicknesses 0 to 40 Å; experimental data are provided for comparison. The thicknesses of




Figure 2. Relation between XPS intensities of C(1s) and Ag(3d), and thicknesses for *n*-alkanethiolate monolayers on silver. Values of C(1s)/Ag(3d) are a function of instrumental parameters; trends are important here. The dashed line displays the theoretical relation given in eq 8 using $K = 1.75$. The thicknesses of the hydrocarbon layer of the monolayers were estimated using eq 9. The solid line represents a linear least-squares fit to the data presented in the figure ($R^2 = 0.994$) for monolayers prepared from $C_nH_{2n+1}SH$ ($n = 11 - 22$).

the hydrocarbon portion of the *n*-alkanethiolate monolayers were estimated by eq 9

$$d = 1.27n \cos \alpha \quad (9)$$

where 1.27 Å is the incremental length per methylene in a trans-extended hydrocarbon chain (a value derived from X-ray data for paraffins),³⁶ *n* is the number of carbons in the alkanethiol, and α is the angle the hydrocarbon chain is canted relative to the surface normal $\approx 12^\circ$ by IR.⁶⁻⁹

In this study we have employed materials that vary from 11 to 22 carbons in the length (or ~ 14 to 27 Å in the thickness) of the hydrocarbon layer. From Figure 2, the relation (eq 8) between $\ln(C/Ag)$ and thickness for thicknesses varying between 14 and 27 Å is virtually linear in accord with experimental data. We thus assume that the midpoint in surface composition -- which would presumably be midway in thickness between the two extremes -- can be estimated from the midpoint of values of $\ln(C/Ag)$.

The systems that we study here, like all previously reported studies of mixed monolayers,^{4,5} are not at thermodynamic equilibrium. Where thermodynamic equilibrium lies in these systems remains an important unresolved question, and we have begun studying the factors -- tail groups, chain lengths, metals, adsorption times, solution concentrations -- that may influence its value. We find that a useful metric against which to compare data from these systems is the ratio of the components in solution ($R_{\text{soln}} = [Sh]_{\text{soln}}/[Lg]_{\text{soln}}$) required to generate a SAM composed of an equimolar mixture of the two components ($R_{\text{SAM}} = [Sh]_{\text{SAM}}/[Lg]_{\text{SAM}}$)

= 1). We present data here in this fashion and compare them with adsorption data obtained on gold under similar conditions.

Results

SAMs on Silver Derived from Different Length

Alkanethiols Terminating in Different Functional Groups:

Sh = CH₃/Lg = CH₂OH and Sh = CH₂OH/Lg = CH₃ from Ethanol.

The properties of SAMs derived from 1 d exposure of freshly evaporated silver to ethanolic solutions (1 mM in total thiol concentration) containing mixtures of two alkanethiols of different chain lengths terminating in different tail groups are given in Figures 3 and 4. For comparisons, data obtained for SAMs on gold prepared under similar experimental conditions are displayed as dotted lines in these figures. In both the Sh = CH₃/Lg = CH₂OH and Sh = CH₂OH/Lg = CH₃ systems, the wettability of SAMs on silver and gold derived from solutions containing the two components ranges between the values obtained on the pure monolayers.³⁷ The SAMs on the two metals formed under similar conditions exhibit differences in wettability and surface composition. The surface compositions of the SAMs formed on silver are closer to the composition of the solution than are the SAMs formed on gold.

In Figure 5, we compare the wetting properties of mixed SAMs on silver and gold. The differences in the wettabilities of SAMs formed on gold and silver from common solutions (Figures 3 and 4) appear to reflect directly the differences in their surface compositions. The data from SAMs on silver and gold are

Figure 3. Monolayers on silver prepared by 1 day exposure to ethanolic solutions containing mixtures of $\text{HS}(\text{CH}_2)_{10}\text{CH}_3$ and $\text{HS}(\text{CH}_2)_{21}\text{CH}_2\text{OH}$ ($\text{Sh} = \text{CH}_3/\text{Lg} = \text{CH}_2\text{OH}$). Solid and open symbols represent advancing and receding contact angles (θ_a and θ_r), respectively; circles and squares represent water and hexadecane, respectively. The solid lines are provided as guides to the eye. The dotted lines represent data obtained under similar conditions with SAMs on gold⁵ and are provided for comparison. The right-hand axis in the lower panel shows the equivalent chain length, n , of a pure monolayer derived from adsorption of $\text{C}_n\text{H}_{2n+1}\text{SH}$ on silver that would yield the same ratio of $\text{C}(1s)/\text{Ag}(3d)$; data on gold are scaled to the right-hand axis in a similar manner from XPS attenuation and ellipsometry data on mixed SAMs. The dashed line in the lower panel represents the adsorption profile expected if the surface composition equalled the solution composition ($R_{\text{SAM}} = R_{\text{soln}}$).





Figure 4. Monolayers on silver prepared by 1 day exposure to ethanolic solutions containing mixtures of $\text{HS}(\text{CH}_2)_{10}\text{CH}_2\text{OH}$ and $\text{HS}(\text{CH}_2)_{21}\text{CH}_3$ ($\text{Sh} = \text{CH}_2\text{OH}/\text{Lg} = \text{CH}_3$). Data are presented as in Figure 3.






Figure 5. Wetting properties of monolayers on silver derived from mixtures of $\text{HS}(\text{CH}_2)_{10}\text{CH}_3$ and $\text{HS}(\text{CH}_2)_{21}\text{CH}_2\text{OH}$ ($\text{Sh} = \text{CH}_3/\text{Lg} = \text{CH}_2\text{OH}$) and of $\text{HS}(\text{CH}_2)_{10}\text{CH}_2\text{OH}$ and $\text{HS}(\text{CH}_2)_{21}\text{CH}_3$ ($\text{Sh} = \text{CH}_2\text{OH}/\text{Lg} = \text{CH}_3$). The surface compositions of the monolayers were estimated by XPS (see text). Larger and smaller points represent data obtained after exposure to solution for 1 d and 1 wk, respectively. Solid and open symbols represent advancing and receding contact angles (θ_a and θ_r), respectively; circles and squares represent water and hexadecane, respectively. The solid lines are provided as guides to the eye; dotted lines represent data obtained on SAMs on gold⁵ and are provided for comparison.



remarkably similar for corresponding values of surface composition (Figure 5).

With continued exposure to a solution containing a mixture of the two thiols, the wetting properties and the compositions of the resulting SAMs change. In the $\text{Sh} = \text{CH}_3/\text{Lg} = \text{CH}_2\text{OH}$ system, the monolayers become more hydrophilic; in the $\text{Sh} = \text{CH}_2\text{OH}/\text{Lg} = \text{CH}_3$ system, they become more hydrophobic. XPS data confirm that the composition of the monolayers have changed; the surface compositions increase in the longer component (see Figure 6). Similar effects have been observed on gold.^{4,5} As with SAMs on gold, the relation between wettability and surface composition is essentially independent of the length of exposure to the contacting solution. This observation indicates that wetting is insensitive to the (we presume small) changes taking place in the structure and composition of the SAM.

SAMs on Silver Derived from Different Length

Alkanethiols Terminating in Common Functional Groups:

$\text{Sh} = \text{CH}_3/\text{Lg} = \text{CH}_3$ and $\text{Sh} = \text{CH}_2\text{OH}/\text{Lg} = \text{CH}_2\text{OH}$ from Ethanol.

The properties of SAMs derived from exposure of silver films to ethanolic solutions containing different length alkanethiols terminating in the same tail group for 1 d (1 mM in total thiol concentration) are given in Figures 7 and 8. The data were obtained under experimental conditions similar to those reported previously on gold; the data obtained on gold are displayed as dotted lines in these figures. The wetting properties of the $\text{Sh} = \text{CH}_3/\text{Lg} = \text{CH}_3$ monolayers by hexadecane, and of the $\text{Sh} = \text{CH}_2\text{OH}/\text{Lg} = \text{CH}_2\text{OH}$ monolayers by water, cannot be described by




Figure 6. Ratio of two different length alkanethiols (C_{11} and C_{22}) required in ethanolic solutions to obtain SAMs of equimolar surface concentration on silver and gold as a function of length of exposure to contacting solution. The total concentration of thiols in each experiment was 1 mM. Data on gold were taken from ref 5. Lines are provided as guides to the eye. Sh and Lg refer to the tail groups of the thiols used in the adsorption: $HS(CH_2)_{10}Sh$ and $HS(CH_2)_{21}Lg$.

Figure 7. Monolayers on silver prepared by 1 day exposure to ethanolic solutions containing mixtures of $\text{HS}(\text{CH}_2)_{10}\text{CH}_3$ and $\text{HS}(\text{CH}_2)_{21}\text{CH}_3$ ($\text{Sh} = \text{CH}_3/\text{Lg} = \text{CH}_3$). Data are presented using the conventions in Figure 3.






Figure 8. Monolayers on silver prepared by 1 day exposure to ethanolic solutions containing mixtures of $\text{HS}(\text{CH}_2)_{10}\text{CH}_2\text{OH}$ and $\text{HS}(\text{CH}_2)_{21}\text{CH}_2\text{OH}$ ($\text{Sh} = \text{CH}_2\text{OH}/\text{Lg} = \text{CH}_2\text{OH}$). Data are presented using the conventions in Figure 3.



arithmetic sums of the interfacial energetics of the tail groups (eq 2 and 3). These deviations require that appreciable disordering of the hydrocarbon chains occurs at the monolayer/liquid interface.

Figure 9 relates the wetting properties of the SAMs formed on silver to their surface compositions. The wetting of the mixed SAMs on silver and gold are similar, for similar surface compositions (% Lg_{SAM}). With continued exposure to the contacting solutions, the composition of these SAMs increase in the longer component (Figure 6); the relation between wettability and surface composition, however, does not change (Figure 9).

Comparison of the Exchange of Metal Thiolates on Silver and Gold with Thiols in Solution. In the four systems of mixed SAMs studied on silver and gold, the surface compositions differed from the solution compositions and were slightly different on the two metals -- SAMs on silver being closer to the composition of the solution. On both metals, the longer component is preferred in the SAMs and its surface concentration increases with continued exposure to the solution (Figure 6). We examined qualitatively the relative rates of exchange on the two metals to determine whether the differences in surface compositions on the two metals could be due to exchange processes.

We prepared pure SAMs of HS(CH₂)₁₁OH and HS(CH₂)₁₁CH₃ on silver and gold. We immersed the SAMs in 1 mM ethanolic solutions of HS(CH₂)₁₁CH₃ and HS(CH₂)₁₁OH, respectively, and measured their wettability by water after various intervals of exposure (Figure 10). The wetting properties of the SAMs change and can be related

Figure 9. Wetting properties of monolayers on silver derived from mixtures of $\text{HS}(\text{CH}_2)_{10}\text{CH}_3$ and $\text{HS}(\text{CH}_2)_{21}\text{CH}_3$ ($\text{Sh} = \text{CH}_3/\text{Lg} = \text{CH}_3$) and of $\text{HS}(\text{CH}_2)_{10}\text{CH}_2\text{OH}$ and $\text{HS}(\text{CH}_2)_{21}\text{CH}_2\text{OH}$ ($\text{Sh} = \text{CH}_2\text{OH}/\text{Lg} = \text{CH}_2\text{OH}$). Data are presented using the conventions in Figure 5.







Figure 10. Exchange of metal-thiolates ($M-S(CH_2)_{11}X$) with thiols ($HS(CH_2)_{11}Y$) in solution; $M = Ag, Au$; $X \neq Y = CH_3, OH$. Pure SAMs derived from $HS(CH_2)_{11}X$ were assembled on silver and gold (circles and squares, respectively) and immersed in 1 mM ethanolic solutions containing $HS(CH_2)_{11}Y$. The samples were removed from solution and the advancing and receding contact angles of water (filled and open symbols) measured. The data are plotted on a scale logarithmic in $\cos \theta$ to demonstrate that the exchange process does not follow first-order kinetics. The lines are provided as guides to the eye.



to the replacement of surface thiolates: the wettability of SAMs on silver and gold prepared from mixtures of $\text{HS}(\text{CH}_2)_{11}\text{OH}$ and $\text{HS}(\text{CH}_2)_{11}\text{CH}_3$ by water is linearly related to the surface composition (eq 2).¹⁴ The rate of replacement of thiolates of one tail group with thiols of another on the two metals is approximately the same. The exchange does not follow first-order kinetics.

On both metals, the replacement of hydroxyl-terminated alkanethiolates by methyl-terminated alkanethiols is slightly faster than that of methyl-terminated alkanethiolates by hydroxyl-terminated alkanethiols on both metals (Figure 10).³⁸ Competitive adsorption experiments of these two alkanethiols for the surfaces of silver and gold from ethanol also show a preference on the surface for the methyl-terminated thiol.¹⁴ We do not presently have a mechanistic model that explains these preferences in detail, but we note that the methyl-terminated surfaces have lower free energies than those terminated by CH_2OH , and are more stable.

Discussion

Comparison of Properties of Mixed SAMs on Silver and Gold. The SAMs formed on silver and gold are similar but not identical in their wetting properties. Are any of the differences due to differences in the structures of the SAMs? Are the structures of the mixed SAMs -- especially the in-plane distribution of components -- different for the same values of R_{SAM} ?

The most pronounced difference on silver and gold is the surface composition of SAMs formed on the two metals under similar conditions (Figures 3, 4, 7 and 8). In brief, although both systems appear not to be at thermodynamic equilibrium, SAMs on silver appear to be more kinetically determined than those on gold (or, put the other way, SAMs on gold are closer to thermodynamic equilibrium than those on silver). The compositions of the SAMs on silver are closer to the composition of the solution from which they were formed than those on gold. When formed from mixtures of long and short thiols, both SAMs on gold and silver contain a higher concentration of the longer component than does the contacting solution. At equilibrium, SAMs containing the longer component would be expected to be the more stable. On both metals, the content of the longer component increases with continued exposure to solution. The SAMs on gold continue to have a higher concentration of the longer component than silver as the time for equilibration with the solution increases (Figure 6).

The differences in composition of SAMs on the two metals must reflect processes occurring during their formation.³⁹ The amount of exchange (Figure 10) that can occur during exposure to a 1 mM ethanolic solution for 1 d (~20 %) is too small to account for the observed compositions of the surface if the initially formed SAM had the composition of the solution. Essentially complete SAMs form from 1 mM solutions in seconds.¹⁶ The factors that affect the composition of the SAM are, therefore, probably important only during the assembly of the monolayer. One possibility is that the

sticking coefficient of the longer alkanethiols on the metals is higher than for shorter thiols.

The chemistry of formation of alkyl thiolates on the two metal surfaces is different. Gold does not form an oxide and its reaction with alkyl thiols, though still not completely understood, probably involves oxidative addition of the thiol to gold and subsequent loss of the hydrogen as H_2 or H_2O .⁴⁰ In contrast, silver oxidizes readily. All of the silver films we have used have thin surface films of oxide before exposure to the solution of alkanethiols, and it is this oxidized surface that reacts with thiols. The resulting SAMs on silver contain no (or very little) silver oxide.⁶ The oxide must be removed during formation of the SAMs either by reduction or displacement by the thiols. The different chemistries that occur on the metal/metal oxide surfaces and not the different structures formed on the two metals are probably responsible for the different surface compositions that result on the two metal surfaces.

Relation Between Wettability and the Structure and Composition of the SAM. The different tilted structures that single-component alkyl thiolate SAMs form on gold and silver are primarily a result of differences in the inter-thiolate distances that are preferred on the metal surfaces.²⁸ The cross-sectional area of a polymethylene chain is 18.4 \AA^2 .⁴¹ On Au(111) (the predominate crystallographic orientation of our polycrystalline samples), alkanethiols adsorb and form a commensurate $(\sqrt{3} \times \sqrt{3})R30^\circ$ overlayer lattice.²²⁻²⁴ The inter-thiolate distance on Au(111) (5.0 \AA) results in an area per chain (21.4 \AA^2) that is greater than

the cross-sectional area of a polymethylene chain by ~15%. As a result, the axis of the hydrocarbon chain tilts ~30° from the surface normal to maximize van der Waals contact between the chains.²⁸ The spacing of *n*-alkyl thiolate SAMs formed on Ag(111) (the predominate crystallographic orientation of our polycrystalline samples)⁶ has not yet been determined. Analogous adsorbates on Ag(111) -- H₂S⁴² and CH₃SSCH₃⁴³ -- adopt higher packing densities of thiolates than the ($\sqrt{3} \times \sqrt{3}$)R30° structure formed on Au(111).^{44,45} As a result, the hydrocarbon chains should require less tilting on silver than on gold to bring the polymethylene chains into van der Waals contact. By IR and other methods, the axis of the hydrocarbon chains on silver have been found to tilt only ~13° from the surface normal.⁶⁻⁹ On both silver and gold, the structure of the metal-thiolate lattice in single-component SAMs and in the mixed SAMs studied here should be the same; the structure of the hydrocarbon region of the SAM near the metal surface should be similar to those of pure SAMs.

Figures 5 and 9 illustrate that the relation between wetting and the composition of the four sets of mixed SAMs studied on silver are extremely similar to those formed on gold ($\Delta\theta \lesssim 10^\circ$). In view of the differences that exist in structure between SAMs on silver and gold (and possibly also in the morphology of the supports), this similarity is remarkable. The wetting properties of the SAMs appear to be determined primarily by the *interfacial composition* of the SAMs. Differences in the details of the structure of the types provided by SAMs on silver and gold do not have a significant influence on wetting.

Experimental

Materials. The alkanethiols were available from previous studies.^{4,14} Abs EtOH (U.S. Industries), Ag wire (Aldrich; 99.99+%), W and Cr-coated W filaments (R. D. Mathis Co.), prepurified Ar (Med-tech; 99.998%, <5 ppm O₂), and dodecanethiol (Aldrich) were used as received. Si(100) wafers (100 mm, Silicon Sense) were cut into 1 x 3 mm slides, rinsed with abs EtOH, and blown dry before use. Contacting solutions (1 mM total thiol concentration) were prepared from N₂ purged abs EtOH.

Preparation of Monolayers. The silver substrates were prepared in a diffusion-pumped thermal evaporator (base pressure = 10⁻⁶ torr). Cr (100 Å) and Ag (~1000 Å) were evaporated individually from resistively heated tungsten filaments onto pre-cut slides of Si(100). Immediately following evaporation, the chamber was backfilled with pre-purified Ar. Slides were transferred to solution under a flow of Ar and were deposited into the various solutions in no set order. The backfill of the chamber and the transfer of slides to all solutions (2 slides per solution) in a run could be accomplished within 7 min after the conclusion of evaporation. Slides were exposed to the ethanolic solutions for 1 d or 1 wk, removed from solution, washed with EtOH and blown dry prior to analysis.

Wetting. Advancing and receding contact angles of water and hexadecane were measured on static drops that had been applied or removed at a constant flow rate (~1 µL/s) using a Matrix Technologies Electro-pipette. The contact angles were measured

using a Ramé-Hart goniometer; the pipet tip was not removed from the drop. Each SAM was characterized with at least three drops of liquid and the contact angles were measured on both sides of the drop. Data presented for 1 day exposure are the average of two sets of these 6 measurements.

X-ray Photoelectron Spectroscopy (XPS). XPS spectra were collected on a Surface Science X-100 XPS spectrometer with a monochromatized Al $K\alpha$ source, concentric hemispherical analyzer, and multichannel detector. The spectra were accumulated at a pass energy of 100 eV, a spot size of 1000 μm , and took <10 min per slide. X-ray-induced damage under these conditions is negligible. The spectra were fit using 80% Gaussian peaks.

XPS was used to measure the thickness of the mixed SAMs (eq 8). Values of $\text{C}(1s)/\text{Ag}(3d)$ were typically within <5 % for SAMs derived from *n*-alkanethiols of a common chain length. SAMs exposed to an adsorbate for 1 wk exhibited values of $\text{C}(1s)/\text{Ag}(3d)$ that were ~10 % greater than those obtained after 1-day exposure.⁴⁶ In Figures 3, 4, 7, and 8, we set the values of $\text{C}(1s)/\text{Ag}(3d)$ obtained for the two pure SAMs in a particular experiment to their respective thicknesses expected from eq 9. Endpoint values from both 1-day and 1-wk exposures were within one unit of *n* of those given in Figure 2. We believe the method used here to determine thicknesses should be applicable to other systems. We recommend use of an XPS peak for the underlying substrate that has a kinetic energy similar to that of the overlayer as the relation (eq 8) between thickness and $\ln(\text{overlayer}/\text{underlayer})$ approximates

linearity at lower values of thickness the closer the values of λ_1 and λ_2 are.

Exchange of Metal Thiolates with Alkanethiols in Solution. SAMs derived from $\text{HS}(\text{CH}_2)_{11}\text{X}$ ($\text{X} = \text{OH}, \text{CH}_3$) on silver and gold were prepared via 1 day exposure to 1 mM ethanolic solutions as previously described.^{6,14} The slides were removed from solution, characterized by wetting and immersed into fresh 1 mM ethanolic solutions of $\text{HS}(\text{CH}_2)_{11}\text{Y}$ ($\text{Y} = \text{CH}_3, \text{OH}; \text{X} \neq \text{Y}$) bearing the other tail group. The slides were periodically removed from solution, characterized by wetting, and reimmersed into the solution. The data presented in Figure 10 are from two independent experiments.

Footnotes and References

1. This research was supported in part by the Office of Naval Research, the Defense Advanced Research Projects Agency, and by the National Science Foundation (Grant CHE-88-12709). XPS spectra were obtained using instrumental facilities purchased under the DARPA/URI program and maintained by the Harvard University Materials Research Laboratory.

2. Reviews of alkanethiolate SAMs on gold: (a) Bain, C. D.; Whitesides, G. M. *Angew. Chem. Int. Ed. Engl.* **1989**, *101*, 522-528. (b) Whitesides, G. M.; Laibinis, P. E. *Langmuir* **1990**, *6*, 87-96.

3. (a) Bain, C. D.; Whitesides, G. M. *J. Am. Chem. Soc.* **1988**, *110*, 3665-3666. (b) Bain, C. D.; Whitesides, G. M. *Science* (Washington, DC) **1988**, *240*, 62-63.

4. Bain, C. D.; Whitesides, G. M. *J. Am. Chem. Soc.* **1989**, *111*, 7164-7175.

5. Folkers, J. P.; Laibinis, P. E.; Whitesides, G. M. unpublished work.

6. Laibinis, P. E.; Whitesides, G. M.; Allara, D. L.; Tao, Y.-T.; Parikh, A. N.; Nuzzo, R. G. *J. Am. Chem. Soc.* **1991**, *113*, 0000-0000.

7. (a) Ulman, A. In *Fourier Transform Infrared Spectroscopy in Colloid and Interface Science*; Scheuing, D. R., Ed.; ACS Symposium Series 447; American Chemical Society: Washington, DC, 1990; 144-159. (b) Walczak, M. M.; Chung, C.; Stole, S. M.; Widrig, C. A.; Porter, M. D. *J. Am. Chem. Soc.* **1991**, *113*, 2370-2378.

8. Bryant, M. A.; Pemberton, J. E. *J. Am. Chem. Soc.* **1991**, *113*, 3629-3637.
9. Fenter, P.; Eisenberger, P.; Li, J.; Camillone III, N.; Bernasek, S.; Scoles, G.; Ramanarayanan, T. A.; Liang, K. S. *Langmuir* in press.
10. Cassie, A. B. D. *Discuss. Faraday Soc.* **1948**, *3*, 11-16.
11. Israelachvili, J. N.; Gee, M. L. *Langmuir* **1988**, *5*, 288-289.
12. Bain, C. D.; Evall, J.; Whitesides, G. M. *J. Am. Chem. Soc.* **1989**, *111*, 7155-7164.
13. (a) Wenzel, R. N. *Ind. Eng. Chem.* **1936**, *28*, 988-994.
(b) Johnson, R. E., Jr.; Dettre, R. H. in *Contact Angles, Wettability, and Adhesion*; Gould, R. F., Ed.; Advances in Chemistry Series 43, American Chemical Society: Washington, DC, 1964; Chapter 7. (c) Dettre, R. H.; Johnson, R. E., Jr. in *Contact Angles, Wettability, and Adhesion*; Gould, R. F., Ed.; Advances in Chemistry Series 43, American Chemical Society: Washington, DC, 1964; Chapter 8.
14. Laibinis, P. E.; Whitesides, G. M. *J. Am. Chem. Soc.* **1991**, *113*, 0000-0000.
15. Nuzzo, R. G.; Allara, D. L. *J. Am. Chem. Soc.* **1983**, *105*, 4481-4483.
16. Bain, C. D.; Troughton, E. B.; Tao, Y.-T.; Evall, J.; Whitesides, G. M.; Nuzzo, R. G. *J. Am. Chem. Soc.* **1989**, *111*, 321-335.
17. Dubois, L. H.; Zegarski, B. R.; Nuzzo, R. G. *J. Am. Chem. Soc.* **1990**, *112*, 570-579.

18. Porter, M. D.; Bright, T. B.; Allara, D. L.; Chidsey, C. E. D. *J. Am. Chem. Soc.* **1987**, *109*, 3559-3568.
19. Harris, A. L.; Chidsey, C. E. D.; Levinos, N. J.; Loiacono, D. N. *Chem. Phys. Lett.* **1987**, *141*, 350-356.
20. Nuzzo, R. G.; Dubois, L. H.; Allara, D. L. *J. Am. Chem. Soc.* **1990**, *112*, 558-569.
21. Nuzzo, R. G.; Korenic, E. M.; Dubois, L. H. *J. Chem. Phys.* **1990**, *93*, 767-773.
22. Helium diffraction: (a) Chidsey, C. E. D.; Liu, G.-Y.; Rowntree, P.; Scoles, G. *J. Chem. Phys.* **1989**, *91*, 4421-4423.
(b) Camillone III, N.; Chidsey, C. E. D.; Liu, G.-Y.; Putvinski, T. M.; Scoles, G. *J. Chem. Phys.* **1991**, *94*, 8493-8502.
23. (a) TEM: Strong, L.; Whitesides, G. M. *Langmuir* **1988**, *4*, 546-558. (b) STM: Widrig, C. A.; Alves, C. A.; Porter, M. D. *J. Am. Chem. Soc.* **1991**, *113*, 2805-2810.
24. X-ray diffraction: Samant, M. G.; Brown, C. A.; Gordon III, J. G. *Langmuir* **1991**, *7*, 437-439.
25. (a) Harris, J.; Rice, S. A. *J. Chem. Phys.* **1988**, *89*, 5898-5908. (b) Hautman, J.; Klein, M. L. *J. Chem. Phys.* **1989**, *91*, 4994-5001.
26. Hautman, J.; Klein, M. L. *J. Chem. Phys.* **1990**, *93*, 7483-7492.
27. Samant et al.²⁴ have estimated the tilt angle of docosyl thiolate on Au(111) by X-ray diffraction to be $12 \pm 1^\circ$. This value has been disputed by Fenter et al.⁹ who also used X-ray diffraction but obtained tilt angles close to values^{6,18,20} obtained by infrared spectroscopy ($\sim 26^\circ$).

28. (a) Ulman, A.; Eilers, J. E.; Tillman, N. *Langmuir* **1989**, *5*, 1147-1152. (b) Bareman, J. P.; Klein, M. L. *J. Phys. Chem.* **1990**, *94*, 5202-5205.

29. Ulman et al. (Tillman, N.; Ulman, A.; Penner, T. L. *Langmuir* **1989**, *5*, 101-111.) have reported differences in the wettability of SAMs on silver and gold derived from HS(CH₂)₁₁OH ($\theta_a^{\text{H}_2\text{O}} \approx 20$ and $<10^\circ$, respectively). We observe that SAMs derived from HS(CH₂)₁₁OH on gold and silver under controlled, anaerobic conditions exhibit common wetting properties ($\theta_a^{\text{H}_2\text{O}} = 10-15^\circ$).¹⁴

30. (a) Hugh, D. B. *Adv. Colloid Interface Sci.* **1980**, *14*, 3-41. (b) Bain, C. D.; Whitesides, G. M. *J. Am. Chem. Soc.* **1988**, *110*, 5897-5898. (c) Wilson, M. D.; Ferguson, G. S.; Whitesides, G. M. *J. Am. Chem. Soc.* **1990**, *112*, 1244-1245.

31. Laibinis, P. E.; Nuzzo, R. G.; Whitesides, G. M. unpublished work.

32. Young, T. *Philos. Trans. R. Soc. London* **1805**, *95*, 65-87.

33. For SAMs derived from two components, $\chi_{\text{Sh}} + \chi_{\text{Lg}} = 1$.

34. Thicknesses of SAMs on gold have been determined by ellipsometry^{3-5,7,18} and XPS attenuation.^{6,14} Ellipsometry requires analysis of the substrate before and after exposure to the adsorbate. This analysis with gold is relatively straightforward technically, since gold does not oxidize. Silver, unlike gold, oxidizes readily and adsorb contaminants upon exposure to air. This reactivity makes analysis difficult.

We^{6,14} have also routinely estimated the relative thicknesses of the SAMs by measuring the attenuation of the XPS signal due to the underlying metal by the SAM. This method has proven successful on

gold but has the disadvantage of being heavily dependent on spectrometer focus and on a stable X-ray source. It also requires an internal standard. The method we employ here avoids these complications and we find it to be a sensitive probe of changes in thickness.

35. The attenuation lengths of photoelectrons of kinetic energies 500-1500 eV in hydrocarbons can be readily estimated by eq i (Laibinis, P. E.; Bain, C. D.; Whitesides, G. M. *J. Phys. Chem.* **1991**, 95, 0000-0000).

$$\lambda \text{ (in \AA)} = 9.0 + 0.022KE \text{ (in eV)} \quad (i)$$

The kinetic energies for photoelectrons for C(1s) and Ag(3d) from Al K α irradiation are 1202 and 1116 eV, respectively. Using eq i, attenuation lengths of 35 and 34 Å are calculated for C(1s) and Ag(3d).

36. Abrahamsson, S.; Larsson, G.; von Sydow, E. *Acta Crystallographica* **1960**, 13, 770-774.

37. The SAMs derived from pure HS(CH₂)₂₁CH₂OH on silver and gold are not wet by water ($\theta_a(\text{H}_2\text{O}) \approx 25^\circ$). SAMs derived from HS(CH₂)_nOH (n = 11, 16, 19) have been reported^{3,14,16,17} to generate monolayers on gold and silver that are wet by water ($\theta_a(\text{H}_2\text{O}) \leq 15^\circ$) while SAMs on gold derived from HS(CH₂)₂₁OH are less hydrophilic ($\theta_a(\text{H}_2\text{O}) \approx 20^\circ$) (Evans, S. D.; Sharma, R.; Ulman, A. *Langmuir* **1991**, 7, 156-161). Although all compounds were reported to be pure by ¹H NMR, the higher molecular weight ω -hydroxy-alkanethiols are more difficult to purify and trace impurities may be responsible for the observed differences in wettability.

38. The change in $\cos \theta_a$, a quantity linearly related to surface composition, is greater in the upper panel of Figure 10 than the lower one.

39. Bain et al.¹² have reported that large differences between surface and solution compositions can be produced on short time scales. Exposure of gold to a solution of $\text{HS}(\text{CH}_2)_{10}\text{CH}_3/\text{HS}(\text{CH}_2)_{11}\text{OH}$ (4:1; $\chi_{\text{OH}} = 0.20$) in isooctane forms SAMs composed primarily of hydroxyl-terminated alkanethiolates ($\chi_{\text{OH}} > 0.95$). The composition of the SAMs derived from 1 min exposure are approximately the same as SAMs derived from 1 wk exposure.

40. For a recent mechanistic study, see Widrig, C. A.; Chung, C.; Porter, M. D. *J. Electroanal. Chem.* in press.

41. (a) Bunn, C. W. *Trans. Faraday Soc.* **1939**, *35*, 482-491.
 (b) Shearer, H. M. M.; Vand, V. *Acta Cryst.* **1956**, *9*, 379-384.
 (c) Wunderlich, B. *Macromolecular Physics Vol. 1*; Academic Press: New York, 1973; p 97.

42. (a) Schwaha, K.; Spencer, N. D.; Lambert, R. M. *Surf. Sci.* **1979**, *81*, 273-284. (b) Rovida, G.; Pratesi, F. *Surf. Sci.* **1981**, *104*, 609-624.

43. (a) Harris, A. L.; Rothberg, L.; Dubois, L. H.; Levinos, N. J.; Dhar, L. *Phys. Rev. Lett.* **1990**, *64*, 2086-2089.
 (b) Harris, A. L.; Rothberg, L.; Dhar, L.; Levinos, N. J.; Dubois, L. H. *J. Chem. Phys.* **1991**, *94*, 2438-2448.

44. Methanethiolate on Ag(111), derived from adsorption of CH_3SSCH_3 , forms a $(\sqrt{7} \times \sqrt{7})R10.9^\circ$ overlayer structure.⁴³ The inter-thiolate spacing (4.42 Å) of this structure, however, results in

an area per chain ($16.9 \text{ \AA}^2/\text{RS}$) that is too small to accomodate a polymethylene chain. Two structures have been observed upon adsorption of H_2S on $\text{Ag}(111)$: $(\sqrt{7} \times \sqrt{7})\text{R}10.9^\circ$ and $(\sqrt{39}\text{R}16.1^\circ \times \sqrt{39}\text{R}16.1^\circ)$.⁴² This latter structure yields an area per chain of $20.3 \text{ \AA}^2/\text{RS}$, larger than the area of a polymethylene chain (18.4 \AA^2)⁴¹ and smaller than the area per chain on $\text{Au}(111)$ ($21.4 \text{ \AA}^2/\text{RS}$).²²⁻²⁴

45. Recent X-ray and helium diffraction studies⁹ of $\text{C}_{22}\text{H}_{45}\text{SH}$ adsorbed on $\text{Ag}(111)$ have determined the adsorbate to be rotated 12.2° from the Ag lattice and have nearest neighbor spacings of $\sim 4.7 \text{ \AA}$ ($\sim 19.1 \text{ \AA}^2/\text{RS}$). These parameters are inconsistent with formation of the $(\sqrt{3} \times \sqrt{3})\text{R}30^\circ$ and $(\sqrt{39}\text{R}16.1^\circ \times \sqrt{39}\text{R}16.1^\circ)$ structures that are observed for adsorption of $\text{CH}_3(\text{CH}_2)_{21}\text{SH}$ on $\text{Au}(111)$ ²²⁻²⁴ and H_2S on $\text{Ag}(111)$.⁴² The structures that form on $\text{Ag}(111)$ are presumably incommensurate.⁹

46. We have reported that continued exposure of alkyl thiolate SAMs on silver to thiols results in formation of a layer of Ag_2S between the SAM and Ag .⁶ We believe the increase in the value of $\text{C}(1s)/\text{Ag}(3d)$ is due to attenuation of the $\text{Ag}(3d)$ signal by the layer of Ag_2S .

Figure Captions

Figure 1. Schematic illustration of an *n*-alkanethiolate monolayer adsorbed on silver.

Figure 2. Relation between XPS intensities of C(1s) and Ag(3d), and thicknesses for *n*-alkanethiolate monolayers on silver. Values of C(1s)/Ag(3d) are a function of instrumental parameters; trends are important here. The dashed line displays the theoretical relation given in eq 8 using $K = 1.75$. The thicknesses of the hydrocarbon layer of the monolayers were estimated using eq 9. The solid line represents a linear least-squares fit to the data presented in the figure ($R^2 = 0.994$) for monolayers prepared from $C_nH_{2n+1}SH$ ($n = 11 - 22$).

Figure 3. Monolayers on silver prepared by 1 day exposure to ethanolic solutions containing mixtures of $HS(CH_2)_{10}CH_3$ and $HS(CH_2)_{21}CH_2OH$ ($Sh = CH_3/Lg = CH_2OH$). Solid and open symbols represent advancing and receding contact angles (θ_a and θ_r), respectively; circles and squares represent water and hexadecane, respectively. The solid lines are provided as guides to the eye. The dotted lines represent data obtained under similar conditions with SAMs on gold⁵ and are provided for comparison. The right-hand axis in the lower panel shows the equivalent chain length, n , of a pure monolayer derived from adsorption of $C_nH_{2n+1}SH$ on silver that would yield the same ratio of C(1s)/Ag(3d); data on gold are scaled to the right-hand axis in a similar manner from XPS

attenuation and ellipsometry data on mixed SAMs. The dashed line in the lower panel represents the adsorption profile expected if the surface composition equalled the solution composition ($R_{\text{SAM}} = R_{\text{soln}}$).

Figure 4. Monolayers on silver prepared by 1 day exposure to ethanolic solutions containing mixtures of $\text{HS}(\text{CH}_2)_{10}\text{CH}_2\text{OH}$ and $\text{HS}(\text{CH}_2)_{21}\text{CH}_3$ ($\text{Sh} = \text{CH}_2\text{OH}/\text{Lg} = \text{CH}_3$). Data are presented as in Figure 3.

Figure 5. Wetting properties of monolayers on silver derived from mixtures of $\text{HS}(\text{CH}_2)_{10}\text{CH}_3$ and $\text{HS}(\text{CH}_2)_{21}\text{CH}_2\text{OH}$ ($\text{Sh} = \text{CH}_3/\text{Lg} = \text{CH}_2\text{OH}$) and of $\text{HS}(\text{CH}_2)_{10}\text{CH}_2\text{OH}$ and $\text{HS}(\text{CH}_2)_{21}\text{CH}_3$ ($\text{Sh} = \text{CH}_2\text{OH}/\text{Lg} = \text{CH}_3$). The surface compositions of the monolayers were estimated by XPS (see text). Larger and smaller points represent data obtained after exposure to solution for 1 d and 1 wk, respectively. Solid and open symbols represent advancing and receding contact angles (θ_a and θ_r), respectively; circles and squares represent water and hexadecane, respectively. The solid lines are provided as guides to the eye; dotted lines represent data obtained on SAMs on gold⁵ and are provided for comparison.

Figure 6. Ratio of two different length alkanethiols (C_{11} and C_{22}) required in ethanolic solutions to obtain SAMs of equimolar surface concentration on silver and gold as a function of length of exposure to contacting solution. The total concentration of thiols in each experiment was 1 mM. Data on gold were taken from

ref 5. Lines are provided as guides to the eye. Sh and Lg refer to the tail groups of the thiols used in the adsorption: $\text{HS}(\text{CH}_2)_{10}\text{Sh}$ and $\text{HS}(\text{CH}_2)_{21}\text{Lg}$.

Figure 7. Monolayers on silver prepared by 1 day exposure to ethanolic solutions containing mixtures of $\text{HS}(\text{CH}_2)_{10}\text{CH}_3$ and $\text{HS}(\text{CH}_2)_{21}\text{CH}_3$ (Sh = CH_3 /Lg = CH_3). Data are presented using the conventions in Figure 3.

Figure 8. Monolayers on silver prepared by 1 day exposure to ethanolic solutions containing mixtures of $\text{HS}(\text{CH}_2)_{10}\text{CH}_2\text{OH}$ and $\text{HS}(\text{CH}_2)_{21}\text{CH}_2\text{OH}$ (Sh = CH_2OH /Lg = CH_2OH). Data are presented using the conventions in Figure 3.

Figure 9. Wetting properties of monolayers on silver derived from mixtures of $\text{HS}(\text{CH}_2)_{10}\text{CH}_3$ and $\text{HS}(\text{CH}_2)_{21}\text{CH}_3$ (Sh = CH_3 /Lg = CH_3) and of $\text{HS}(\text{CH}_2)_{10}\text{CH}_2\text{OH}$ and $\text{HS}(\text{CH}_2)_{21}\text{CH}_2\text{OH}$ (Sh = CH_2OH /Lg = CH_2OH). Data are presented using the conventions in Figure 5.

Figure 10. Exchange of metal-thiolates ($\text{M-S}(\text{CH}_2)_{11}\text{X}$) with thiols ($\text{HS}(\text{CH}_2)_{11}\text{Y}$) in solution; M = Ag, Au; $\text{X} \neq \text{Y} = \text{CH}_3, \text{OH}$. Pure SAMs derived from $\text{HS}(\text{CH}_2)_{11}\text{X}$ were assembled on silver and gold (circles and squares, respectively) and immersed in 1 mM ethanolic solutions containing $\text{HS}(\text{CH}_2)_{11}\text{Y}$. The samples were removed from solution and the advancing and receding contact angles of water (filled and open symbols) measured. The data are plotted on a scale logarithmic in $\cos \theta$ to demonstrate that the exchange

process does not follow first-order kinetics. The lines are provided as guides to the eye.

TECHNICAL REPORT DISTRIBUTION LIST (June 1991)

Office of Naval Research
Chemistry Division, Code 1113
800 North Quincy Street
Arlington VA 22217-5000

Dr. James S. Murday
Chemistry Division, Code 6100
Naval Research Laboratory
Washington DC 20375-5000

Dr. Robert Green, Director
Chemistry Division, Code 385
Naval Weapons Center
China Lake CA 93555-6001

Dr. Eugene C. Fischer
Code 2840
David Taylor Research Center
Annapolis MD 21402-5067

Dr. Elek Lindner
Naval Ocean Systems Center
Code 52
San Diego CA 92152-5000

Commanding Officer
Naval Weapons Support Center
Attn: Dr. Bernard E. Doua
Crane IN 47522-5050

Dr. Richard W. Drisko
Naval Civil Engineering Laboratory
Code L52
Fort Hueneme CA 93043

Dr. Harold H. Singerman
David Taylor Research Center
Annapolis MD 21402-5067
ATTN: Code 283

Chief of Naval Research
Special Assistant for Marine Corps Matters, Code 00MC
800 North Quincy Street
Arlington VA 22217-5000

Defense Technical Information Center
Building 5, Cameron Station
Alexandria VA 22314

ABSTRACT DISTRIBUTION LIST (June 1991)

Prof. Robert W. Armstrong
Department of Chemistry
University of California
405 Hilgard Avenue
Los Angeles CA 90024

Dr. Joseph Boyer
Department of Chemistry
University of New Orleans
New Orleans LA 70148

Professor Jerald S. Bradshaw
Department of Chemistry
Brigham Young University
Provo UT 84602

Prof. Ronald Breslow
Department of Chemistry
Columbia University
New York NY 10027

Dr. Duncan W. Brown
Advanced Technology Materials
520-B Danbury Road
New Milford CT 06776

Prof. Cynthia J. Burrows
Department of Chemistry
State University of New York
Stony Brook NY 11794-3400

Professor Peter Chen
Department of Chemistry
Harvard University
Cambridge MA 02138

Prof. Anthony W. Czarnik
Department of Chemistry
Ohio State University
120 West 18th Avenue
Columbus OH 43210-1173

Prof. Peter Dervan
Department of Chemistry
Calif Institute of Technology
Pasadena CA 91125

Prof. Francois N. Diederich
Department of Chemistry
University of California
405 Hilgard Avenue
Los Angeles CA 90024

Prof. Dennis A. Dougherty
Department of Chemistry
Calif Institute of Technology
Pasadena CA 91125

Prof. Kenneth M. Doxsee
Department of Chemistry
University of Oregon
Eugene OR 97403

Prof. Margaret C. Etter
Department of Chemistry
University of Minnesota
207 Pleasant Street SE
Minneapolis MN 55455

Prof. Wilmer K. Fife
Department of Chemistry
Indiana Univ/Purdue Univ
1125 East 38th Street
Indianapolis IN 46223

Prof. Samuel H. Gellman
Department of Chemistry
University of Wisconsin
Madison WI 53706

Prof. Thomas J. McCarthy
Department of Polymer Science
University of Massachusetts
701 Graduate Research Center
Amherst MA 01003

Prof. Arthur E. Martell
Department of Chemistry
Texas A&M University
College Station TX 77843-3255

Prof. William L. Mock
Department of Chemistry
University of Illinois at
Chicago
Chicago IL 60680

Prof. Martin E. Newcomb
Department of Chemistry
Texas A&M University
Box 3578
College Station TX 77843-3255

Prof. Peter Schultz
Department of Chemistry
University of California
Berkeley CA 94720

Prof. Carol Venanzi
Department of Chemistry
New Jersey Inst of Technology
323 King Blvd.
Newark NJ 07102

Prof. Howard W. Whitlock
Department of Chemistry
University of Wisconsin
Madison WI 53706

Prof. Jeffrey D. Winkler
Department of Chemistry
The University of Chicago
5735 S. Ellis Avenue
Chicago IL 60637